

GENERAL

EPORITE 5250-1 A / B is a two - components epoxy potting and sealing system which is recommended for potting and encapsulating of electronic components.

The cured EPORITE 5250-1 A / B exhibits excellent, physical properties and heat stability.

STORAGE

Store A & B parts at temperature lower than 30°C but not less than 5°C. Keep the containers at dry place & sealed tightly.

<u>HANDLING AND</u> <u>SAFETY</u>

Gloves and glasses are suggested for user's personal protection. Clean with soap and water when skin contact.

PROCESSING

- 1. Well mixed with mixing ratio A:B = 100:40 by weight.
- 2. Potting/casting associated with vacuum process.
- 3. Curing condition at $60 \sim 80^{\circ}$ C for 2 ~ 4hr.

NOTE: The process can be adjusted according to the specific manufacturing process or performance requirement.

SPECIFICATION

Specification	EPORITE 5250-1A	EPORITE 5250-1B
Chemical Type	Epoxy Resin	Modified Polyamide
Appearance	Black Liquid	Yellowish Liquid
Specific Gravity	1.1 ± 0.1	1.0 ± 0.2
Viscosity (25°C)	2500 ± 625 cps	100±50 cps
Mixing Ratio (by weight)	100	40
Shelf Life (25°C)	6 months	6 months
Mixing Viscosity (25°C)	800 ± 200 cps	
Pot Life (25°C)	82 min/126 g	
Gel Time (80°C)	13 min/10 g	
Curing Condition	25° C/24 hr or 60 ~ 80° C/2 ~ 4 hr	

<u>PROPERTIES OF THE CURED RESIN</u>**

Property	EPORITE 5250-1 A / B		
Hardness (Shore D)	80~90		
Glass Transition Temperature (°C)	<40		
Coefficient of Thermal Expansion (mm/ mm/°C)	$(\alpha_1) 70 \sim 90 \times 10^{-6}$ $(\alpha_2) 160 \sim 220 \times 10^{-6}$		
Moisture absorption (wt %)	< 0.5		
** Curing Condition: 80°C // hr			

** Curing Condition: 80°C/4 hr

REMARK

The information contained is believed to be reliable and only for the reference without any effective guarantee for the application of the user. The user is responsible to determine the suitability for the user's application and the reliability of the products. Epolab Chemical will not accept claim of warranties of the fitness or reliability for a particular purpose especially the liability for consequential damages of end products.



No. 11, Ho-Jiun N. Rd., Chung-Li Ind. Park, Chung-Li, Taoyuan 320, Taiwan Tel: 886-3- 4521501~3 Fax: 886-3-4529318 service@epolab.com.tw www.epolab.com