


EPORITE



EPORITE EHM-241

GENERAL

EPORITE EHM-241 is a one-component epoxy hot melt system recommended especially for fiber-reinforced prepreg.

The cured EPORITE EHM-241 exhibits excellent physical properties such as mechanical strength, and heat stability.

STORAGE

Store EPORITE EHM-241 at temperature lower than 5°C.

HANDLING AND SAFETY

Gloves and glasses are suggested for user's personal protection. Clean with soap and water when skin contact.

PROCESSING

1. Coating process: 70 ~75°C
2. Impregnation process: 100~105°C
3. Storage: lower than 5°C
4. Molding process: 150°C/ 0.5~1 hr + 150°C/ 2~2.5 hr.

*Above all temperatures are suggested temperatures.

NOTE: The process can be adjusted according to the specific manufacturing process or performance requirement.

SPECIFICATION

Specification	EPORITE EHM-241
Chemical Type	Epoxy Compound
Appearance	White solid
Specific Gravity	1.2± 0.1
Viscosity (70°C)	17500 ± 6500 cps
Shelf Life	6 months (5°C) or 1 month (25°C)
Gel Time (150°C)	< 5 min/0.2g
Glass Transition Temperature (°C)	170 ~ 190

PROPERTIES OF THE CURED RESIN

Specimen Information:

TC-36-12K, 24T, RC 40% Prepreg, Unit-dimension (0°), Molding thickness: 3.1mm

Mechanical Property	EPORITE EHM-241
Flexure Strength (Mpa)	> 1400
Young's Modulus (Gpa)	> 130
Tensile stress (MPa)	> 1000

REMARK

The information contained is believed to be reliable and only for the reference without any effective guarantee for the application of the user. The user is responsible to determine the suitability for the user's application and the reliability of the products. Epolab Chemical will not accept claim of warranties of the fitness or reliability for a particular purpose especially the liability for consequential damages of end products.



EPOLAB CHEMICAL INDUSTRIES INC.

No. 11, Ho-Jiun N. Rd., Chung-Li Ind. Park, Chung-Li, Taoyuan 320, Taiwan

Tel : 886-3-4521501~3 Fax : 886-3-4529318 service@epolab.com.tw www.epolab.com