


EPORITE



EPORITE P77 A / B

GENERAL

EPORITE P77 A / B is a two-components epoxy coating system which is recommended as the primer for fiber reinforced composite or metal.

The cured coating exhibits very good adhesive strength and excellent impact resistance.

STORAGE

Store A & B parts at temperature lower than 30°C but not less than 5°C. Keep the containers at dry place & sealed tightly.

HANDLING AND SAFETY

Gloves and glasses are suggested for user's personal protection. Clean with soap and water when skin contact.

PROCESSING

1. Well mixed with mixing ratio A:B = 2:1 by weight. Dilute with suitable solvent.
2. Spray coating with curing condition 60 ~ 80°C/0.5 ~ 1 hr.

NOTE: The process can be adjusted according to the specific manufacturing process or performance requirement.

SPECIFICATION

Specification	EPORITE P77A	EPORITE P77B
Chemical Type	Epoxy Resin	Polyamide
Appearance	Clear Liquid	Light Yellow Liquid
Specific Gravity	1.1 ± 0.1	0.9 ± 0.1
Viscosity (25°C)	13000 ± 3250 cps	100 ± 50 cps
Mixing Ratio (by weight)	2	1
Shelf Life (25°C)	6 months	6 months
Mixing Viscosity (25°C)	1800 ± 600 cps	
Pot Life (25°C)	144 min/150 g	
Dry Time (80°C)	11 min/0.2 g (thin coating)	
Curing Condition	60 ~ 80°C/1 ~ 2 hr	

PROPERTIES OF THE CURED RESIN

Property	EPORITE P77 A / B
Hardness (Shore D)	70 ~ 80
Glass Transition Temperature (°C)	40 ~ 60
Coefficient of Thermal Expansion (mm/ mm/°C)	(α_1) 75 ~ 95 × 10 ⁻⁶ (α_2) 180 ~ 240 × 10 ⁻⁶
Moisture absorption (wt %)	< 0.5
Impact Test (30 cm)	Pass

REMARK

The information contained is believed to be reliable and only for the reference without any effective guarantee for the application of the user. The user is responsible to determine the suitability for the user's application and the reliability of the products. Epolab Chemical will not accept claim of warranties of the fitness or reliability for a particular purpose especially the liability for consequential damages of end products.



EPOLAB CHEMICAL INDUSTRIES INC.

No. 11, Ho-Jiun N. Rd., Chung-Li Ind. Park, Chung-Li, Taoyuan 320, Taiwan

Tel : 886-3- 4521501~3 Fax : 886-3-4529318 service@epolab.com.tw www.epolab.com